

AD-A269 817



AD

TECHNICAL REPORT ARCCB-TR-93027

**SELF-ORGANIZED CRITICALITY AND THE
BARKHAUSEN EFFECT IN AMORPHOUS AND
POLYCRYSTALLINE METALS**

PAUL J. COTE
LAWRENCE V. MEISEL

DTIC
ELECTE
SEP 27 1993
S E D

JULY 1993



**US ARMY ARMAMENT RESEARCH,
DEVELOPMENT AND ENGINEERING CENTER
CLOSE COMBAT ARMAMENTS CENTER
BENÉT LABORATORIES
WATERVLIET, N.Y. 12189-4050**



APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

93 9 24 1 1 0

93-22287



248

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacturer(s) does not constitute an official indorsement or approval.

DESTRUCTION NOTICE

For classified documents, follow the procedures in DoD S200.22-M, Industrial Security Manual, Section II-19 or DoD S200.1-R, Information Security Program Regulation, Chapter IX.

For unclassified, limited documents, destroy by any method that will prevent disclosure of contents or reconstruction of the document.

For unclassified, unlimited documents, destroy when the report is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE July 1993		3. REPORT TYPE AND DATES COVERED Final	
4. TITLE AND SUBTITLE SELF-ORGANIZED CRITICALITY AND THE BARKHAUSEN EFFECT IN AMORPHOUS AND POLYCRYSTALLINE METALS				5. FUNDING NUMBERS AMCMS: 6111.02.H611.1	
6. AUTHOR(S) Paul J. Cote and Lawrence V. Meisel					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army ARDEC Benet Laboratories, SMCAR-CCB-TL Watervliet, NY 12189-4050				8. PERFORMING ORGANIZATION REPORT NUMBER ARCCB-TR-93027	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army ARDEC Close Combat Armaments Center Picatinny Arsenal, NJ 07806-5000				10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES Presented at the International Conference on the Physics of Transition Metals, Darmstadt, Germany, 20-24 July 1992. Published in the Conference Proceedings.					
12a. DISTRIBUTION AVAILABILITY STATEMENT Approved for public release; distribution unlimited				12b. DISTRIBUTION STATEMENT	
13. ABSTRACT (Maximum 200 words) An investigation of the possibility that the Barkhausen effect in amorphous and polycrystalline ferromagnets is an example of self-organized criticality is described. Since the theory of self-organized criticality was introduced by Bak, Tang, and Wiesenfeld to explain the behavior of spatially extended, dissipative, dynamical systems, the Barkhausen effect is a natural candidate for such a description. The data are consistent with self-organized critical behavior: the power spectral densities depend on frequency f as $1/f^2$ and the distribution of pulse energies are well described by a power law analogous to the Gutenberg-Richter law for earthquakes. Alternative explanations for power-law dependences are also presented.					
14. SUBJECT TERMS Barkhausen Effect, Self-Organized Criticality, Power-Law Distributions, Ferromagnetism, Amorphous Metal				15. NUMBER OF PAGES 6	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL		

TABLE OF CONTENTS

INTRODUCTION	1
EXPERIMENTAL	1
THEORY	2
ANALYTIC PROCEDURE	3
RESULTS	3
DISCUSSION	4
REFERENCES	5

List of Illustrations

1. Distribution of pulse energies for the Metglas sample	3
2. Power spectral density from Eq. (1) (circles) and from FFT (line) for Metglas	4

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

DTIC QUALITY INSPECTED 1

INTRODUCTION

Bak, Tang, and Weisenfeld (ref 1) (BTW) introduced the concept of self-organized criticality (SOC) to explain power-law distributions and flicker noise in events associated with spatially extended, dissipative, dynamical systems such as earthquake faults. Jensen, Christensen, and Fogedby (ref 2) (JCF) clarified the analysis connecting power-law dependences and power spectral densities.

SOC has been explored through computer simulations of sandpile dynamics (ref 1), plastic flow in metals (ref 3), and earthquakes (ref 3). Experimental investigations include studies of actual sandpile dynamics (ref 4), sliding friction (ref 5), magnetic transitions in garnet films (ref 6), and the magnetic Barkhausen effect in an amorphous ferromagnetic alloy (ref 7).

Barkhausen phenomena appear to be ideal for description in terms of SOC and have many features in common with other SOC-related processes such as plastic deformation in metals and slip-stick at earthquake faults. In ferromagnets, (magnetic) hysteresis is produced by magnetic domains and their response to applied fields: for low applied fields, kinetic barriers permit only small reversible domain wall extensions and the system remains magnetically "elastic"; when the applied field is large enough to overcome these barriers (coercive force), the system enters a magnetically "plastic" regime characterized by large, random, irreversible domain wall jumps. These jumps generate Barkhausen noise, which may be detected by a coil placed near the sample. Magnetic hysteresis is analogous to mechanical hysteresis.

A brief summary of the results of a study of the Barkhausen effect as an example of SOC in three ferromagnetic materials: an iron base glassy metal, polycrystalline iron, and a nickel base polycrystalline alloy, alumei, is presented herein. A more extensive report has been published elsewhere (ref 8).

The data on the three materials are consistent with SOC. The distributions of pulse energy releases are well described by power laws with exponents similar to the Gutenberg-Richter law for earthquake distributions and the power spectral densities vary with frequency f as $1/f^\alpha$ (flicker noise). Furthermore, the distributions of pulse durations and areas also follow power laws, and the pulse distributions exhibit "size-effect" cutoffs at large amplitudes similar to those seen in sandpile simulations (ref 9).

EXPERIMENTAL

The amorphous alloy is a nominal 2-mil thick ribbon of Metglas 2605S ($\text{Fe}_{78}\text{B}_{13}\text{Si}_9$) from Allied-Signal cut into approximately 2-mm by 20-mm strips. The iron and alumei ($\text{Ni}_{65}\text{Al}_3\text{Mn}_2$) specimens were assorted lengths of 5 mil thermocouple wire obtained from Omega Engineering.

The samples were placed within a pickup coil located at the center of an air-core solenoid. A signal generator provided the sinusoidal current to the solenoid, which produces a field that continuously drives the sample through its B-H loop. The pickup coil registered trains of pulses that were amplified and recorded by a digital oscilloscope. The scan rate was selected to maintain suitable separation of individual pulses, while also providing an adequate number of pulses per train for analysis (typically 200).

THEORY

The central idea of SOC is that extended, dissipative, dynamical systems tend to evolve into critical states in which chain reactions of all sizes in time and space propagate through the system. Computer simulations indicate that the main features of SOC systems are power-law distributions of chain reaction sizes, $1/f^\alpha$ power spectral densities, and fractal structures.

JCF show that the power spectral density of a train of uncorrelated pulses (where each pulse represents a chain reaction) can be expressed as

$$S(f) = \frac{r}{(\pi f)^2} \int_0^\infty d\tau G(\tau) \sin^2(2\pi f\tau) \quad (1)$$

where r is the pulse repetition rate and $G(T)$ is a weighted distribution of lifetimes, defined as

$$G(T) = \int_0^\infty dA P(A,T) [A/T]^2 \quad (2)$$

where $P(A,T)$ is the joint probability for a pulse to have area A and length T . The equations hold for any distribution of uncorrelated pulses.

The present data are consistent with a simple power-law distribution of pulse lifetimes (as expected with SOC) modified by a sharp cutoff "size-effect." That is,

$$G(T) = T^\alpha H(T - T_c) \quad , \quad \text{for } t_0 < T < \infty \quad (3)$$

where $H(x)$ is the Heaviside function and the "size-effect" cutoff on pulse size is T_c . Such distributions of lifetimes yield (ref 10) power spectral density having the following form:

1. for

$$1/T_0 < f < 1/t_0 \quad , \quad S(f) \sim f^{-(3+\alpha)} \quad \text{when } \alpha < -1 \quad (4a)$$

$$\sim f^{-2} \quad \text{when } \alpha > -1 \quad (4b)$$

2. for

$$f < 1/T_0 \quad , \quad S(f) \approx \text{constant}. \quad (4c)$$

JCF obtained similar results for an exponential cutoff "size-effect."

ANALYTIC PROCEDURE

The following steps were followed:

1. A systematic procedure for selecting a baseline and critical signal level was adopted to allow an unambiguous definition of individual pulses.
2. Pulse durations, areas, and energies were computed for each pulse.
3. Joint probability distributions $P(A,T)$ and distributions of durations $G(T)$ were computed from the area and duration data.
4. Power spectral densities were also determined directly via Fourier transform techniques (FFT algorithms, etc.).

RESULTS

A sampling of typical results is presented in this section. Figure 1 shows the distribution of Barkhausen pulse energies for the Metglas specimen: the power law with sharp cutoff at large pulse energies is illustrated. The power-law exponent is -1.60. Similar results are obtained for the iron and alumei samples with exponents -1.44 and -1.58, respectively. The distributions of pulse areas, durations, and weighted distributions of lifetimes (Eq. (2)) all follow similar power-law dependences.




Figure 1. Distribution of pulse energies for the Metglas sample.

The results of Figure 2 illustrate the excellent agreement between power spectra for Metglas computed from pulse distributions via Eq. (1) and that obtained with FFT; the form of the power spectral density is consistent with Eq. (4).




Figure 2. Power spectral density from Eq. (1) (circles) and from FFT (line) for Metglas.

DISCUSSION

Power-law distributions and $1/f^2$ dependences in the power spectra in these three very different ferromagnets suggest that the Barkhausen effect is an example of SOC phenomena. Furthermore, the resemblance of the Barkhausen distribution of energies and the distribution of earthquake energies (ref 3) suggests that they may belong to the same universality class.

However, another interpretation may be viable. As Mandelbrot (ref 11) has emphasized, fractal structure or fragmentation also gives rise to power-law distributions. Thus, complex pre-existing microstructure and the distribution of magnetic domains within the microstructure could follow a power law, which could then give rise to the observed power-law pulse distributions in the Barkhausen effect independent of SOC. (For example, Hornbogen (ref 12) has demonstrated the applicability of fractals to microstructures in metals.) Since Eqs. (1) through (4) would still apply, the power spectral density would also have the $1/f^2$ form characteristic of SOC under this interpretation. We will examine this possibility in future work.

REFERENCES

1. P. Bak, C. Tang, and K. Wiesenfeld, *Phys. Rev. Lett.*, Vol. 59, 1987, p. 381.
2. H.J. Jensen, K.C. Christensen, and H.C. Fogedby, *Phys. Rev. B*, Vol. 40, 1989, p. 7425.
3. K. Chen, P. Bak, and S.P. Obukhov, *Phys. Rev. A*, Vol. 43, 1991, p. 625.
4. G.A. Held, D.H. Solina II, D.T. Keane, W.J. Haag, P.M. Horn, and G. Grinstein, *Phys. Rev. Lett.*, Vol. 65, 1990, p. 1120.
5. H.J.S. Feder and J. Feder, *Phys. Rev. Lett.*, Vol. 66, 1991, p. 2669.
6. K.L. Babcock and R.M. Westervelt, *Phys. Rev. Lett.*, Vol. 64, 1990, p. 2168.
7. P.J. Cote and L.V. Meisel, *Phys. Rev. Lett.*, Vol. 67, 1991, p. 1334.
8. L.V. Meisel and P.J. Cote, *Phys. Rev. B*, Vol. 46, 1992, p. 10822.
9. L.P. Kadenoff, S.R. Nagel, L. Wu, and S.-M. Zhou, *Phys. Rev. A*, Vol. 39, 1989, p. 6524.
10. L.V. Meisel and P.J. Cote, to be published in: *Computers in Physics*.
11. B.B. Mandelbrot, *Fractal Geometry of Nature*, Freeman, New York, 1983.
12. E. Hornbogen, *Int. Mat. Revs.*, Vol. 34, 1989, p. 277.

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	NO. OF COPIES
CHIEF, DEVELOPMENT ENGINEERING DIVISION	
ATTN: SMCAR-CCB-DA	1
-DC	1
-DI	1
-DR	1
-DS (SYSTEMS)	1
CHIEF, ENGINEERING SUPPORT DIVISION	
ATTN: SMCAR-CCB-S	1
-SD	1
-SE	1
CHIEF, RESEARCH DIVISION	
ATTN: SMCAR-CCB-R	2
-RA	1
-RE	1
-RM	1
-RP	1
-RT	1
TECHNICAL LIBRARY	5
ATTN: SMCAR-CCB-TL	
TECHNICAL PUBLICATIONS & EDITING SECTION	3
ATTN: SMCAR-CCB-TL	
OPERATIONS DIRECTORATE	1
ATTN: SMCWV-ODP-P	
DIRECTOR, PROCUREMENT DIRECTORATE	1
ATTN: SMCWV-PP	
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1
ATTN: SMCWV-OA	

NOTE: PLEASE NOTIFY DIRECTOR, BENET LABORATORIES, ATTN: SMCAR-CCB-TL, OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST

	NO. OF COPIES		NO. OF COPIES
ASST SEC OF THE ARMY RESEARCH AND DEVELOPMENT ATTN: DEPT FOR SCI AND TECH THE PENTAGON WASHINGTON, D.C. 20310-0103	1	COMMANDER ROCK ISLAND ARSENAL ATTN: SMCRI-ENM ROCK ISLAND, IL 61299-5000	1
ADMINISTRATOR DEFENSE TECHNICAL INFO CENTER ATTN: DTIC-FDAC CAMERON STATION ALEXANDRIA, VA 22304-6145	12	MIAC/CINDAS PURDUE UNIVERSITY P.O. BOX 2634 WEST LAFAYETTE, IN 47906	1
COMMANDER US ARMY ARDEC ATTN: SMCAR-AEE	1	COMMANDER US ARMY TANK-AUTMV R&D COMMAND ATTN: AMSTA-DDL (TECH LIB) WARREN, MI 48397-5000	1
SMCAR-AES, BLDG. 321	1	COMMANDER	
SMCAR-AET-O, BLDG. 351N	1	US MILITARY ACADEMY	1
SMCAR-CC	1	ATTN: DEPARTMENT OF MECHANICS	
SMCAR-CCP-A	1	WEST POINT, NY 10996-1792	
SMCAR-FSA	1		
SMCAR-FSM-E	1	US ARMY MISSILE COMMAND	
SMCAR-FSS-D, BLDG. 94	1	REDSTONE SCIENTIFIC INFO CTR	2
SMCAR-IMI-I (STINFO) BLDG. 59	2	ATTN: DOCUMENTS SECT, BLDG. 4484	
PICATINNY ARSENAL, NJ 07806-5000		REDSTONE ARSENAL, AL 35398-5241	
DIRECTOR US ARMY BALLISTIC RESEARCH LABORATORY ATTN: SLCBR-DD-T, BLDG. 305	1	COMMANDER US ARMY FGN SCIENCE AND TECH CTR ATTN: DRXST-SD	1
ABERDEEN PROVING GROUND, MD 21005-5066		220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	
DIRECTOR US ARMY MATERIEL SYSTEMS ANALYSIS ACTV ATTN: AMXSY-MP	1	COMMANDER US ARMY LABCOM	
ABERDEEN PROVING GROUND, MD 21005-5071		MATERIALS TECHNOLOGY LAB ATTN: SLCMT-IML (TECH LIB)	2
DIRECTOR US ARMY RESEARCH LABORATORY ATTN: AMSRL-WT-PD (DR. B. BURNS)	1	WATERTOWN, MA 02172-0001	
ABERDEEN PROVING GROUND, MD 21005-5066			

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER, US ARMY AMCCOM, ATTN: BENET LABORATORIES, SMCAR-CCB-TL, WATERVLIET, NY 12189-4050, OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST (CONT'D)

	NO. OF COPIES		NO. OF COPIES
COMMANDER US ARMY LABCOM, ISA ATTN: SLCIS-IM-TL 2800 POWDER MILL ROAD ADELPHI, MD 20783-1145	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/MN EGLIN AFB, FL 32542-5434	1
COMMANDER US ARMY RESEARCH OFFICE ATTN: CHIEF, IPO P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709-2211	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/MNF EGLIN AFB, FL 32542-5434	1
DIRECTOR US NAVAL RESEARCH LAB ATTN: MATERIALS SCI & TECH DIVISION CODE 26-27 (DOC LIB) WASHINGTON, D.C. 20375	1 1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER, US ARMY AMCCOM, ATTN: BENET LABORATORIES, SMCAR-CCB-TL, WATERVLIET, NY 12189-4050, OF ANY ADDRESS CHANGES.